## DEWAL® SHEER QUALITY

## DeWAL® DW203

## Unsintered PTFE product

Features and Benefits:

- Exceptional chemical resistance and extreme temperature range
- Low coefficient of friction
- Non-stick properties
- Excellent drape characteristics
- Good strength after sintering
- Chemically inert
- Pigments available to match EIA colors



DeWAL® DW 203 is ideal for:

- Cable insulation and harness wrap
- Dielectric medium for co-axial cables
- Gaskets, valve seals, and diaphragms

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Backing Material		Extruded PTFE
Density, g/cc	ASTM-D792	1.5
Thickness, inches, (mm)	ASTM-D374	0.002 - 0.020
		(0.0508 - 0.508)
Tensile Strength, psi, (MPa)	ASTM-D6040/882	2250
	@ 0.002"	(15.5)
Peak Elongation, %	ASTM-D6040/882	30
Dielectric Strength, V/mil	@ 0.002" ASTM-D149 @ 0.002"	2350
Operational Temperature Range		-450 °F / +500 °F (-268 °C / +260 °C)
PACKING SPECIFICATIONS		
Width, inches, (mm)	N/A	0.375" – 8" Flat Pad 0.156" - 0.876" Solid Pack
Core Diameter, inches, (mm)	N/A	3
		(76.2)
Core Type	N/A	Plastic & Cardboard Available
Max Roll O.D., inches, (mm)	N/A	11
		(279.4)
Packaging Type	N/A	Flat or Solid Pack



The information contained in this document is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this document will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers DeWAL products for each application. The Rogers logo, DeWAL logo and DeWAL are trademarks of Rogers Corporation or one of its subsidiaries. © 2018 Rogers Corporation. All rights reserved. 0918-PDF • Publication #175-028