

DeWAL[®] DW402P Skived UHMW-PE Film

DeWAL[®] DW402P is a skived microporous Ultra High Molecular Weight Polyethylene (UHMW) film.

It has a highly uniform pore structure in the X,Y and Z directions, an open-cell structure and can be rendered hydrophilic through surface treatments.

Applications:

- Gas and liquid filtration
- Medical diagnostic test kits
- Low dielectric constant wrap
- Batteries

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Base Film		UHMW-PE
Density, g/cc	ASTM-D792	0.60
Thickness, mm, (inches)	ASTM-D374	0.13 – 1.6 (0.005 – 0.062)
Tensile Strength, MPa, (psi)	ASTM-D6040/882	16.89
	@ 0.005"	(1000)
Peak Elongation, %	ASTM-D6040/882	35
Pore Size Distribution microns	PMI	5-50
Void Volume, % nominal		30
Heat Distortion Temperature, °C, (°F)		95
		(203)
Maximum Operating Temperature, °C, (°F)		93
		(200)
PACKING SPECIFICATIONS		
Maximum Width, mm, (inches)	N/A	710
		(28)
Core Diameter, mm, (inches)	N/A	76.2
		(3)
Max Roll O.D., mm, (inches)	N/A	330
		(13)

All metric conversions are approximate. Additional technical information is available.

Typical values should not be used for specification limits.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers DeWAL products for each application. The Rogers logo, DeWAL logo and DeWAL are trademarks of Rogers Corporation or one of its subsidiaries. © 2018 Rogers Corporation. All rights reserved. 1218-PDF • Publication #175-094