

GRISWOLD
GripON
 Less Slip. More Grip.

With Acrylic PSA

Features and benefits of Griswold Cellular Rubber Materials

- Natural rubber is inherently anti-slip with a high coefficient of friction
- Polyolefin finish provides increased bonding ability
- Extremely resistant to abrasion and tear
- Available in flexible roll or sheet good formats

PROPERTY	TEST METHOD	SPECIFICATION
Typical Physical Properties	The data reported is for sponge only	
Density, Average kg/m ³ (lb/ft ³)	ASTM D1056	655 (41)
Thickness, mm (inches) *Tolerances	ASTM D1056	1.27 (0.050) *1.143 - 1.524 (0.045 - 0.060)
Standard Color		Black
Polymer		Natural Rubber/SBR
Compression Deflection, min kPa (psi)	ASTM D1056 @ 25% compression	152 (22)
Compression Deflection Change after Oven Aging, %	ASTM D1056 168 hrs @ 70°C (158°F)	+ 25
Compression Set, % max	ASTM D1056 50% deflection @ 70°C (158°F)	60
Substrate	Micro-porous Polyolefin Double Coated Polyester Film	

Notes:

- All metric conversions are approximate
- Additional technical information is available
- Values should not be used for specification limits