



For a lasting impression.

In the Long Run, the Difference is the Cushion.

Speed, quality and price – you know that's what your customers look for from a flexographic print run. And one of the most important factors in delivering all three is often overlooked: the cushion mounting tape.

A Unique Open-Cell Urethane Cushion

The key is our unique open-cell urethane technology. Our urethane cells "bounce back" to their original state instead of breaking down under the constant pounding of your presses. So the tape you remove in demount has the same qualities as the tape you mounted in set up. The result is millions of high-quality impressions.

The Value of Consistency – Over Millions of Impressions

The consistent performance of R/bak SA 2000 means you can make millions of impressions at faster speeds without making adjustments. You save time, money and aggravation.

The Right Cushion for Each Job – from Solids to Screens

R/bak SA 2000 tapes deliver award-winning quality for all your flexographic print jobs. With three levels of compressibility, R/bak SA 2000 offers the right cushion for precise results across the board, from line to process.

Better Print Quality from Start to Finish


With R/bak SA 2000 cushion mounting tapes you can run even the largest jobs, knowing the results will be there. Because only the compressibility of R/bak open-cell urethane holds up to the rigors of flexographic printing.

Stop wasting time and money making on-press adjustments to achieve the results your customers demand. Instead, make a single business adjustment: change your tape to R/bak SA 2000. And deliver quality time and time again.

As Run-time Increases, the Superior Quality of R/bak SA 2000 Remains Consistent.



Initial print quality with R/bak SA 2320 tape.



Initial print quality with medium PE tape.



R/bak SA 2320 print quality after 1 hour and 45 minutes, with no adjustments.




Medium PE tape print quality after 1 hour and 45 minutes, with no adjustments.


The above information on R/bak SA 2000 tapes represents typical values. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose. The relative merits of materials for a specific application should be determined by your evaluation.

The Science Behind the Art of Better Flexographic Results.

The big quality difference between R/bak SA 2000 and other tapes can best be seen by taking a microscopic look inside the foam. Open-cell urethane bounces back over and over again so that the tape provides the same level of cushioning no matter how many times it is compressed. Closed-cell polyethylene breaks down in use, not bouncing back and resulting in loss of ink density.



Open-cell urethane structure (magnified 100 times) naturally bounces back to deliver consistent results.



Closed-cell polyethylene's structure (magnified 100 times) changes with repeated use and requires repeated adjustments.



R/bak SA 2000 open-cell



Closed-cell polyethylene foam



Open-cell structure "springs' recover after compression



"Balloons" or closed-cell structure ruptures under over-impression



Original performance



Loss of impression force and reduced resiliency

The Adhesive Difference.

The SA 2000 products utilize specially developed acrylic adhesive chemistry.

Repositioning -

R/bak SA 2000 allows for easy repositioning of plate and tape during make-ready

Improved solvent resistance –

acrylics stand up to alcohols and acetates commonly used in printing

Easier handling -


adhesive releases easily if contacted to itself

Complete removability -

no adhesive transfer to plates or cylinders

Peel Strength Performance of R/bak SA 2000 Adhesive System

The Dyna Peel test uses a method similar to Pressure Sensistive Tape Council procedure PSTC.00101.10 to better simulate on-press performance



R/bak SA 2000 Plate-Side Adhesive Solvent Resistance

rate-side Adhesiv	re Solvent Resistance						
Solvent	Performance						
Water-Based Ink Cleanup (20%)	Excellent — no effect on PSA or plate hold-down ability						
lsopropyl Alcohol	Good — minor swelling of adhesive, no effect on plate hold-down ability						
n-propyl Alcohol	Good — moderate swelling of adhesive, no effect on plate hold-down ability						
Ethyl Alcohol	Fair — minor swelling of adhesive, some effect on plate hold-down ability						
80:20 Solution of n-propyl Alcohol and n-propyl Acetate	Good — minor swelling of adhesive, no effect on plate hold-down ability						
Methyl-ethyl Keytone	Good — minor swelling of adhesive, no effect on plate hold-down ability						
Toluene	Good — moderate swelling of adhesive, no effect on plate hold-down ability						

KEVLAR is a registered trademark of E.I. du Pont de Nemours and Company or its affiliates.

A Cushion to Improve the Quality, Run-Time and Cost Benefit of any Flexographic Application.

R/bak° SA 2000 comes in three levels of compressibility to handle the complete range of flexographic printing, from process and fine screens to heavy solids.


And compressibility is important. Compressibility, not density, determines performance on press.


The chart below gives you the specifications for each of three families of R/bak SA 2000 cushion mounting tapes to help you determine which tape is best for a particular print job.

R/bak SA 2000 tapes:

- ¥ Easy-on, easy-off acrylic adhesive
- ¥ Provide consistent print quality
- ¥ Color-coded for easy identification in the press room

Compressibility – not Density – Determines Performance on Press.





R/bak SA 2000	Film Dot (%)											
Compressibility Selector Guide	Benefits and Applications	Color Name	Foam Type	Adhesive Type	Tape Thickness	Typical Con @15%	mpressibility @25%	Max. Use Temp.	Printed Dot Samples	Positive Text Samples	Reversed Text Samples	
	R/bak SA 2100 Soft Combination SA 2115 & SA 2120— 15 & 20 mil tapes for combination jobs with demanding process and screen work	Chino	Open-Cell Microcellular Urethane	Differential Acrylic	\$A 2115— 0.015" (0.38 mm) \$A 2120— 0.020" (0.51 mm)*	SA 2115— 10 psi (0.7 kg/cm²) SA 2120— 10 psi (0.7 kg/cm²)	SA 2115 — 13 psi (0.9 kg/cm²) SA 2120 — 13 psi (0.9 kg/cm²)	150 _i F (66 _i C)		4 point 1 nt Times R imes R	nt Times R	
	R/bak SA 2300 General Purpose SA 2315 & SA 2320 — 15 & 20 mil tapes for combination jobs with screen, line and solid work	Deerskin	Open-Cell Microcellular Urethane	Differential Acrylic	\$A 2315— 0.015" (0.38 mm) \$A 2320— 0.020" (0.51 mm)*	SA 2315 — 17.5 psi (1.2 kg/cm²) SA 2320 — 17.5 psi (1.2 kg/cm²)	\$A 2315 — 22 psi (1.5 kg/cm²) \$A 2320 — 22 psi (1.5 kg/cm²)	150 _i F (66 _i C)		4 point 1 nt Times R imes R	nt Times R	
	R/bak SA 2500 Firm Combination SA 2520— 20 mil topes for line and solid work with darker screens	Bone	Open-Cell Microcellular Urethane	Differential Acrylic	SA 2520— 0.020" (0.51 mm)*	SA 2520— 28 psi (2.0 kg/cm²)	SA 2520— 45 psi (3.2 kg/cm²)	150 _i F (66 _i C)		4 point . nt Times R Times P	nt Times R	

^{*} Thicknesses are listed as nominal thickness for printing operations.

The above information on R/bak SA 2000 tapes represents typical values. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose. The relative merits of materials for a specific application should be determined by your evaluation.

The Mechanics of a Successful Flexographic Print Run.



Insure cylinder is clean prior to mounting tape. Allow sufficient time for cleaning solution to dry.



Apply tape to cylinder using light pressure with the palm of your hand or a squeegee. Avoid using fingertips as this will apply uneven pressure and increase likelihood of bubbles.



Insure that the back of the plate is clean prior to mounting.



Apply plate to cylinder using the same method described above for the tape.



For long runs with aggressive plate-cleaning techniques use edge seal to insure trouble-free operation.



High Performance Foams Division 245 Woodstock Road Woodstock, CT 06281-1815 U.S.A.

Phone: 860.928.3622 Fax: 860.928.7843

Rogers N.V. Gent, Belgium Phone: +32.9.2353611 Fax: +32.9.2353658

Rogers Japan Inc. Tokyo, Japan Phone: +81.3.5200.2700

Fax: +81.3.5200.0571

Hong Kong SAR, PRC Phone: +852.2549.7806 Fax: +852.2549.8615 Fax: +852.2549.4576

Rogers Southeast Asia, Inc.

Rogers Taiwan, Inc. Taipei, ROC

Phone: +886.2.8660.9056 Fax: +886.2.8660.9057

Rogers Korea, Inc. Seoul, ROK Phone: +82.31.716.6112 Fax: +82.31.716.6208

Rogers Technologies (Singapore) Inc.

Singapore

Phone: +65.6747.3521 Fax: +65.6747.7425

Rogers China, Inc. Guangzhou, PRC Phone: +86.20.8363.4612 Fax: +86.20.8363.4490 Rogers Technologies (Suzhou) Co., Ltd.

Suzhou, PRC

Phone: +86.512.6258.8000 Fax: +86.512.6258.1278

Rogers Shanghai International Trading Co., Ltd. Shanghai, PRC

Phone: +86.21.6391.6088 Fax: +86.21.6391.5060

Distributed by:



The Rogers Corporation High Performance Foams, Woodstock Facility, Woodstock, CT is registered to ISO 9001:2000 Certificate No. A-3843

www.rogerscorporation.com